



Thermal Conductivity Enhancement of Iraqi Origin Paraffin Wax by Nano-Alumina

Miqdam T. Chaichan*

Rasha Mohammed Hussein**

Aida Mohammed Jawad***

*Energy and Renewable Energies/ University of Technology

**Department of Mechanical Engineering/University of Technology

***The Middle Technical University

*Email: 20185@uotechnology.edu.iq

**Email: mechanicalflower99@yahoo.com

***Email: aida200899@yahoo.com

(Received 7 November 2016; accepted 22 February 2017)

<https://doi.org/10.22153/kej.2017.02.003>

Abstract

Paraffin wax is utilized for the heat storage applications taking advantage from the high stored latent heat during the phase change (from solid to fluid) period. What isn't right with this procedure is that the wax has a little heat transfer rate because of its low thermal conductivity. The thermal conductivity improvement of the paraffin wax has been examined utilizing nano-material with high thermal conductivity. In the recent study, (Al_2O_3) nanoparticles with weights of 1, 2, and 3% of the paraffin wax were added to the paraffin wax. The Iraqi paraffin wax accessible at the local markets was utilized as a phase change material (PCM).

Many properties of the wax were changed due to the addition of nanofillers. The wax color was changed from light brown to white. The thermal conductivity of the paraffin wax was expanded by increasing the additional nanoparticles extent with 37.1, 42.3 and 60.32% for 1, 2 and 3% added nano- Al_2O_3 compared to pure wax conditions. The subsequent change in the thermal conductivity of the paraffin wax makes it reasonable for the use in thermal storage applications.

Keywords: Latent heat, Nano-alumina, Paraffin wax, Thermal storage,

1. Introduction

The world's vitality circumstance came to an intersection, and the subject of whether there is a different option to the small oil assets or not [1]. The ascent in oil costs demonstrates the recorded decay of oil assets. The renewable energy sources, for example, nuclear power, solar energy, wind energy, and other renewable energies, as hydrogen fuel cells can get to be feasible contrasting options to fossil fills later on. Many valuable studies upheld the assessment that the end of the oil time is coming following a couple of decades [2]. With the unpredictability of the issue, the affirmation of this suspicion is far with the advancement of

innovations used to produce oil and gas in various parts of the world [3]. To exploit solar energy is an impediment to specialists, as the solar radiation oscillates with the time and the dilemma of using it around evening hours. In this way, enhancing the thermal storage will diminish the effect of sunlight oscillation. The improvement in the energy storage of any system will increase its effectiveness and expand the consistent quality, and it assumes a critical part in keeping up the delivered energy [4].

The phase change materials are utilized to store thermal energy in solar energy applications. Variable phase change materials (PCM) have high latent heat storage capacities at the stage of phase

change period from a solid to a fluid state, or from the fluid to the solid state. During this process, this material can store around 5 to 14 times the energy per unit volume, contrasted to the sensible heat storage materials, such as water, stone masonry, or rock.

Its low thermal conductivity portrays paraffin wax as other PCMS. This character limits the absorption and energy release rate. Many researchers have utilized variable sorts of fillers with high thermal conductivity to enhance the effective thermal conductivity of the phase change material. Fukai abused ceramic powder fillers and graphitic carbon fiber [5], Pincemin utilized graphite particles [6], Kim used peeled graphite as a part of his works [7], and Elgafy employed carbon nanofibers [8].

Current nanomaterials show physical and chemical properties contrast essentially when compared to the base mass structure [10]. The generation of various sorts of nanoparticles has ended up less demanding as a result of the fast advance in nanotechnology [11], mechanical and electronic building, and current procedures [12 and 13]. The higher thermal conductivity of the nanomaterials created from metals or metal oxides can be utilized with low conductivity materials as PCMs to improve its thermal conductivity [14]. A higher thermal conductivity can be accomplished at smaller nanomaterials size. The enhanced of thermal conductivity of PCMS causes advancements in its thermal qualities [15].

Wang figured out how to include nanomaterials for paraffin wax without bringing about any surface strain. The outcomes demonstrated that the expansion of nano-TiO₂ in paraffin wax bringing on an adjustment in the thermal limit of the phase change material. The thermal conductivity of the wax additionally expanded plainly [16].

Fan researched the impact of including different extents of carbon nanofillers on the courier and energy storage and thermal properties of materials utilizing paraffin (PCMS). The thermal capacity of the formed material was slightly less with the nano-fillers addition; however, it has no impact on the temperature of the phase change. The outcomes demonstrated that the thermal conductivity of the PCMS nanocomposite increments with the expansion of the extent of fillers. Likewise, the relative change in the thermal conductivity relies upon the size and state of the added nanoparticles material [17]. Chaichan added two types of nano materials to the paraffin wax in variable mass fractions. Al₂O₃ and TiO₂ were used to improve the thermal

conductivity of the used PCM. The results indicated that thermal conductivity was improved with increasing the nanofillers mass fraction. The results revealed significant enhancement in the wax's charging and discharging period which was reduced with the addition of nanofillers [18]. The use of nano materials-paraffin wax composite gets wider interest in different applications, especially those related to the uses of solar thermal applications [19 & 22].

The present study demonstrates the test examination of the performance enhancement due to the expansion of Al₂O₃ nanoparticles in the paraffin wax in various weights. The essential objective of this study is to assess the best proportion of nanoparticles that can be added to Iraqi paraffin wax to improve its thermal conductivity.

2. Experimental Setup

2.1. Experimental Procedure

The Iraqi paraffin wax was picked as PCM in the present study. It was selected due to its nominal melting point around 45°C. Table 1 gives the details of the thermal and physical properties of the utilized wax. Nano-Alumina with grain size from 30 to 60 nm was used in this work. Table 2 demonstrates the details of the suppliers and properties of this material. These materials were chosen as a result of its accessibility and low costs; and were utilized with no additional purification procedures as got from the supplier. The technique for blending the wax with nanoparticles can be partitioned into five phases:

1. Pre-dissolving of unadulterated PCMs (as they received by the provider), it was melted to perform the homogeneous immaculate material. The fluid paraffin has been filled in Vials to facilitate the handling in the next stages. The material has been chilled off at room temperature; the paraffin wax was pre-melted and degassed in a vacuum stove at 105°C for 3 hours.
2. The nano-material and the paraffin wax were weighed to prepare the correct samples. The nano-fillers samples with mass fractions of 1, 2 and 3% wt. were prepared.
3. The nano-material was dried at the same condition of the wax in the oven.
4. The samples of nano-Al₂O₃- PCM prepared using a melting mixing procedure. At first, the nanomaterial added to the molten wax with required percentage, and strong shear mixing with a magnetic stirrer for 15 min was used to

mix the nano-Al₂O₃ totally. This process was followed by an intense shaking using an ultrasonic shaker for five hours. The used ultrasonic shaker used type AlabTech (EXXX_1000), which picture is illustrated in Fig. 1. The process was conducted by putting the required nano- alumina fraction with the wax in a closed vessel immersed in 65°C hot water. Each sonication run of the devise was set to be 99 minutes. The samples temperatures were maintained at 65 °C during the mixing process to confirm the liquid phase of the wax.



Fig. 1. Ultrasonic shaker type AlabTech (EXXX-1000).

After the complete mixing of wax and nano-Al₂O₃, it was followed by the solidification process. The mixture was poured in a circular template with dimensions of 2 cm dia., and then was allowed to solidify freely at room temperature (25°C) to form a solid paraffin wax. This solidification process completed at about three hours.

Table 1,
Thermo-Physical Properties for the Iraqi Paraffin Wax [18]

Material properties		
Melting temperature	(°C)	44 °C
Latent heat of fusion	(kJ/kg)	190
Solid density	(kg/m ³)	930
Liquid density	(kg/m ³)	830
Thermal conductivity	(W/m °C)	0.21
Specific heat (Solid)	(kJ/kg °C)	2.1
Specific heat (Liquid)	(kJ/kg °C)	2.1

Table 2,
The suppliers and the used nano-fillers specifications

Item	Al ₂ O ₃ specifications
Manufacturer	Yurui Chemical Co., Ltd
Appearance	White powder
Assay	99.99%
PH value	7.5
Crystal and Type	a
Grain size nm	30-60 nm
bulk density %	0.43
Loss on drying %≤	0.21
Sulfated assay %≤	0.42
Fe ≤ ppm	≤0.005%
Si ≤ ppm	≤0.003%
Mg ≤ ppm	≤0.001%

2.2. Experimental Instruments

The following instruments were used in the tests:

1. The scanning electron microscopy (SEM) was used to display the surface micrographs of representative wax-nano Al₂O₃ samples. Fig 2 shows the main parts of the SEM that is the electron column, detectors, scanning system, and vacuum system, display, and electronics controls. The Electron microscopy can generate the electron beam on the surface of the sample with a size spot up to 10 nm diameter, and holds the remains sufficient current to form an acceptable image.
2. Hot Disk Thermal Constants Analyzer (Fig. 3) was used to measure the thermal conductivity of the samples. This device has a sensor plane passing hot consists of an electrically conducting pattern etched into the chip of thin nickel. This spiral is located between two sheets of insulation Mica material. When the thermal conductivity measurement is performed, the aircraft sensor hot disk is fixed between two pieces of the sample facing the sensor surface. By passing an electric current high enough to cause an increase in the sensors temperature, and is at the same time, recording the temperature increase with time.

Every test was repeated three times and the average was taken as the representative reading. The standard deviations of the data found to be less than 2% for the measurements.

2.3. Test Procedure

The tests began by setting up the wax tests. The second step was to get quick examples of

nano-filler and wax suspensions. After the preparing the specimens, the thermal conductivity tests were begun utilizing Hot Disk Thermal Constants Analyzer. Both the softening and cooling practices were tried by warming the specimens in a compartment to 65°C and the abandon it to cool by natural convection in the air which its temperature was kept up at 25°C. The wax and wax-nano composite tests temperature were measured and recorded amid every period. The outcomes were analyzed and discussed.



Fig. 2. The scanning electron microscopy (SEM).



Fig. 3. Hot Disk Thermal Constants Analyzer.

3. Results and Discussion

The mixing of nanoparticles with wax results in a change in the color of the wax as shown in Fig. 4 (A and B). The color of the wax has turned from light brown (Fig. 4 A) to faint white color (Fig. 4 B). The proper mixing of the material with nanoparticles means the nano- Al_2O_3 entered within the paraffin wax composition thus changing its characteristics. Among these features is the wax color. The color of the wax changing gives a clear indication of good mixing between the nanoparticles and wax. The nano-wax composite's color was affected slightly by the nano-alumina fraction variation.




Fig. 4. (A) The paraffin wax before mixing with nano- Al_2O_3 and (B) after the mixing

Fig. 5 represents the wax-nano Al_2O_3 suspension surface nature as it seems by the SEM scanning. The figure indicates that the nano-alumina-paraffin wax has non porous structure. It appears as one phase shape of the structure in (Fig. 5A), and any difference may seem in Figs. 5 B & C are due to the non-crystallite between wax and nano- Al_2O_3 . The figures reveal acceptable dispersion of the nanomaterial into the wax. This dispersion at 100nm scale was with few nano Al_2O_3 agglomerations, but it has a strong interaction between wax and the nanoparticles. The distributions at 50nm scale (Fig. 5 B) and 20nm range (Fig.5 C) manifest strong interaction between both materials.




Fig. 5. scanning emission microscopic test (SEM) of the paraffin wax-nano Al₂O₃ suspension

The temperature impact on the thermal conductivity of the paraffin wax and its nano-Al₂O₃ composites is outlined in Fig. 6. Adding nano-alumina to the wax increased its thermal conductivity as the figure reveals. The phenomenon of higher thermal conductivity of the nano-Al₂O₃-PCM composite than the case of wax alone resulted from lower thermal resistance. Also, the figure clearly shows that the thermal conductivity of the tested materials is temperature dependent, as its thermal conductivity decreased

with increasing temperature. The paraffin thermal conductivity achieved its insignificant at the melting point, and after this stage, it came back to rise. The paraffin wax thermal conductivity was influenced by the expansion of nano-Al₂O₃. The nano-Al₂O₃ expansion enhanced the heat exchange rates by 37.1, 42.3 and 60.32% for 1, 2 and 3% added nano-Al₂O₃. The liquefying change period from solid to fluid brought on a decrease in the thermal conductivity through this time. Table 3 illustrates the experimental results.

Table 3, The experimental results.

Temperature (°C)	Thermal conductivity			
	Paraffin wax	PW+1% nano Al ₂ O ₃	PW+2% nano Al ₂ O ₃	PW+3% nano Al ₂ O ₃
25	0.08894	0.09382	0.099101	0.1073
35	0.05817	0.076043	0.079022	0.091001
45	0.037898	0.06109	0.0635	0.07102
55	0.044367	0.0712	0.07327	0.087107
65	0.047897	0.0782	0.079902	0.088108

Fig. 7 demonstrates that the nanoparticles enhanced the thermal conductivity of the paraffin wax yet this upgrade was changing with the additional nano-Al₂O₃ fraction. Gharagozloo [23] presented a relation of the relative thermal conductivity improvement by the condition:

$$\text{Relative improvement} = (k - k_0)/k_0$$

This relation quantitatively connects the capability of thermal conductivity increment with the nanomaterial quantity. Nano-Al₂O₃-wax suspension accomplished an extensive change. It is hard to compare between various literatures findings because of the usage of variable paraffin wax types and nano-particle sizes.

Fig. 7 shows a comparison between the present results and the data reported in the literature. Enhancement in the thermal conductivity is evident whatever the type of the wax depending on the nano-Al₂O₃ quantity added with the addition of other parameters as the nanomaterial

size, shape, and distribution figure. Arusu [24] improved the paraffin wax by adding nano-alumina particles and compared the variation in thermal conductivity with pure paraffin wax.




Fig. 6. Thermal conductivity during the temperature variation for the wax and nano-Al₂O₃-wax composites.




Fig. 7. Relative enhancement in thermal conductivity due to the added nano-fillers.

The relative enhancement in the thermal conductivity in Arusu case was lower than that of the recent study. This variation can be returned to the used paraffin wax difference. Arusu used a wax with 321°C melting point while the recent study used 45°C melting point wax. Table 4 lists the thermal conductivity relative enhancements for the Arusu and recent study.

Table 4, The thermal conductivity enhancement variation for recent study and Ref. [24]

Mass Fraction (%)	Recent study thermal conductivity enhancement rate (%)	Arusu [20] thermal conductivity enhancement rate (%)
0	0	0
1	0.1817	0.122
2	0.21237	0.167
3	0.303	0.246

4. Conclusions

In this study, the nano- Al_2O_3 particles were blended with an Iraqi paraffin wax to create a composite phase change materials (PCM) described with high latent heat and high thermal conductivity. The produced material had many properties changed from the first one. The material shading has been modified from chestnut to white. The SEM test demonstrated a decent scattering of the nano- Al_2O_3 in the wax. The thermal conductivity was expanded with the expansion in the nano-molecule mass division. The relative improvement with mass segment increment was 60.32% for 3% mass portion

expansion of nano- Al_2O_3 . The other published papers results showed some minor contrasts because of the utilized wax properties and to the employed nano- Al_2O_3 size and shape.

5. References

- [1] Al-Maamary H M S, Kazem H A and Chaichan M T, Changing the energy profile of the GCC States: A review, International Journal of Applied Engineering Research, vol. 11, No. 3, pp. 1980-1988, 2016.
- [2] BP. BP Statistical Review of World Energy June 2012. IOC statistical report, London: BP, 2012.
- [3] Fitzpatrick, M., Assessment of climate change impacts on key terrestrial ecosystems and species in the Arabian Gulf countries, Technical Concept Note prepared for the Phase II Work Programme on Climate Change Vulnerability and Adaptation, EAD, 2012.
- [4] Sharma A, Tyagi V V, Chen C R, Buddhi D, Review on thermal energy storage with phase change materials and applications, Renewable and Sustainable Energy Reviews, vol. 13, pp. 318–345, 2009.
- [5] Fukai J, Kanou M, Kodama Y, Miyatake O, Thermal conductivity enhancement of energy storage media using carbon fibers, Energy Convers Manage., vol. 41, pp. 1543-1556, 2000.
- [6] Pincemin S, Olives R, Py X, Highly conductive composites made of phase change materials and graphite for thermal storage, Solar Energy Materials and Solar Cells, vol. 92, pp. 603-613, 2008.
- [7] Kim S, Drzal L T, High latent heat storage and high thermal conductive phase change materials using exfoliated graphite nanoplatelets, Solar Energy Materials and Solar Cells, vol. 93, pp. 136-142, 2009.
- [8] Elgafy A, Lafdi K, Effect of carbon nano-fiber additives on thermal behavior of phase change materials, Carbon, vol. 43, pp. 3067-3074, 2005.
- [9] Abdel-Hameed S A M, Margha F H, Preparation, crystallization behavior and magnetic properties of nanoparticles magnetic glass-ceramics in the systems Fe_2O_3 - CoO - MnO_2 , Fe_2O_3 - NiOMoO_3 and Fe_2O_3 - CoO - V_2O_5 . Journal of Non-Crystalline Solids, vol. 358, No. 4, pp. 832-838, 2012.
- [10] Cabeza L F, Gutierrez A, Barreneche C, Ushak S, Fernández A G, Fernández A I, Grágeda M, Lithium in thermal energy

- storage: A state-of-the-art review, *Renewable and Sustainable Energy Reviews*, vol. 42, pp. 1106–1112, 2015.
- [11] Cannio M, Bondioli F, Mechanical activation of raw materials in the synthesis of Fe₂O₃-ZrSiO₄ inclusion pigment, *Journal of the European Ceramic Society*; vol. 32, No. 3, pp. 643-647, 2012.
- [12] Zhang D M, Zang C H, Zhang Y S, Han Y H, Gao C X, Yang Y X, Electrical property of nano-crystalline gamma-Fe₂O₃ under high pressure, *Physical B-Condensed Matter*, vol. 407, No. 6, pp.1044-1046, 2012.
- [13] Fan G, Li H, Cao L, Shan F, Preparation and thermal properties of form-stable palmitic acid/active aluminum oxide composites as phase change materials for latent heat storage, *Materials Chemistry and Physics*, vol. 137, No. 9, pp. 558-564, 2012.
- [14] Gil A, Barreneche C, Moreno P, Solé C, Fernández A I, Cabeza L F, Thermal behavior of D-mannitol when used as PCM: Comparison of results obtained by DSC and in a thermal energy storage unit at pilot plant scale, *Applied Energy*, vol. 111, pp. 1107–1113, 2013.
- [15] Giro-Paloma J, Rayon E, Roa J J, Martinez M, Fernandez A I, Effect of the filler on the nano mechanical properties of polypropylene in contact with paraffinic phase change material, *European Polymer Journal* vol. 63, pp. 29–36, 2015.
- [16] Wang J, Xie H, Guo Z, Lia Y, Improved thermal properties of paraffin wax by the addition of TiO₂ nanoparticles, *Proceedings of the 2nd International Workshop on Heat Transfer Advances for Energy Conservation and Pollution Control (IWHT2013)*, October 18-21, 2013.
- [17] Fan L W, Fang X, Wang X, Zeng Y, Xiao Y Q, Yu Z T, Xu X, Hu Y C, Cen K F, Effects of various carbon nano-fillers on the thermal conductivity and energy storage properties of paraffin-based nano-composite phase change materials, *Applied Energy*, vol. 110, pp. 163–172, 2013.
- [18] Chaichan M T, Kamel S H, Al-Ajeely A N M, Thermal conductivity enhancement by using nano-material in phase change material for latent heat thermal energy storage systems, *SAUSSUREA*, vol. 5, No. 6, pp. 48-55, 2015.
- [19] Zeng J L, Gan J, Zhu F R, Yu S B, Xiao Z L, Yan W P, Zhu L, Liu Z Q, Sun L X, Cao Z, Tetradecanol/expanded graphite composite form-stable phase change material for thermal energy storage, *Solar Energy Materials & Solar Cells*, vol. 127, pp. 122–128, 2014.
- [20] Chaichan M T, Al-Hamdani A H, Kasem A M, Enhancing a Trombe wall charging and discharging processes by adding nano-Al₂O₃ to phase change materials, *International Journal of Scientific & Engineering Research*, vol. 7, No. 3, pp: 736-741, 2016.
- [21] Rathod M K, Banerjee J, Thermal stability of phase change materials used in latent heat energy storage systems: A review, *Renewable and Sustainable Energy Reviews*, vol. 18, pp. 246-258, 2013.
- [22] Abdin Z, Alim M A, Saidur R, Islam M R, Rashmi W, Mekhilef S, Wadi A, Solar energy harvesting with the application of nanotechnology, *Renewable and Sustainable Energy Reviews*, vol. 26, pp. 837–852, 2013.
- [23] Gharagozloo P E, Eaton J K, Goodson K E, Diffusion, aggregation, and the thermal conductivity of nanofluids, *Applied Physical Letters*, vol. 93, No. 10, pp. 103-110, 2008.
- [24] Arasu V, Mujumdar A S, Numerical study on melting of paraffin wax with Al₂O₃ in a square enclosure, *International Communications in Heat and Mass Transfer*, vol. 39, pp. 8-16, 2013.

تحسين الموصلية الحرارية لشمع البرافيين العراقي المنشأ باضافة الألومينا النانوية المنشأ

مقدم طارق جيجان* رشا محمد □ سين** عائدة محمد جواد***

*مركز تكنولوجيا الطاقة والطاقت المتجددة / الجامعة التكنولوجية

** قسم الهندسة الميكانيكية/ الجامعة التكنولوجية

***الكلية التقنية/ جامعة الوسط التقنية- بغداد

*البريد الإلكتروني: 20185@uotechnology.edu.iq**البريد الإلكتروني: mechanicalflower99@yahoo.com***البريد الإلكتروني: aida200899@yahoo.com

الخلاصة

يستخدم الشمع البارافيني مادة خازنة للحرارة ذات طاقة كامنه بالأفاده من الحرارة الكامنه لة خلال مرحلة تغير الطور (من صلب الى مائع). من مساوي هذه المادة معدلات انتقال حرارة قليله عند عمليات الإنصهار/التجمد بسبب انخفاض الموصلية الحرارية لها. تمت دراسة تحسين الموصلية الحرارية للشمع البارافيني باستخدام مادة نانوية ذات توصيل حراري مرتفع. إذ تمت في هذه الدراسة اضافة مادة الألومينا (Al_2O_3) النانوية بنسب وزنية من ١، ٢، ٣% الى الشمع البارافيني عراقي الإنتاج. تم استخدام شمع برافيني عراقي متوفر بالأسواق المحليه بوصفه مادة متغيرة الطور (PCM). لوحظ تغير عدة خواص للشمع بسبب اضافة المادة النانوية. إذ تغير لون الشمع من اللون البني الى الأبيض. أن الموصلية الحرارية للشمع البارافيني ارتفعت بزيادة نسبة المادة النانوية الوزنية. كما تحسنت معدلات الشحن وتفريغ الشحن للطاقة الحرارية بشكل واضح باضافة المادة النانوية الى الشمع بنسب ١، ٢، ٣، ٤، ٥، ٦، ٧، ٨، ٩، ١٠% عند اضافة نانو المونيا بنسب وزنية ١، ٢، ٣% مقارنة بحالة استخدام شمع بمفرده. إن هذا التحسن في الموصلية الحرارية للشمع البارافيني يمنح هذه المادة افضلية الاستخدام في تطبيقات الخزن الحراري للطاقة.