

Synthesis, Characterization and Optical Properties of New Pvc- Amines Polymers

Ahmed A. Ahmed

Polymer Research Unit, College of Science, Al-Mustansiriyah University
Baghdad-Iraq.

Abstract

Poly (vinyl chloride) (PVC) react with different amines in THF to form new polymers (PVC-L). The structures of these polymers have been characterized by IR and Uv-Vis. spectrophotometry. The optical properties of pure and modified PVC were studied in the region (200-400 nm). The optical data analyzed and interpreted in term of the theory of phonon assisted direct electronic transition; it is observed that the energy is affected by doping type polymers used.

Keywords: PVC, optical properties, Energy gap.

Introduction

Modification of polymers has received greater attention to bring specific properties to the modified material, such as enhanced thermal stability, multiphase physical responses, compatibility, impact response, flexibility, and rigidity[1]. A number of ligands including polydentate amines, crown ethers, phosphines and bipyridines have been bound with mainly polystyrene divinylbenzene copolymers [2-3]. These studies are mostly concerned with ion-binding and catalytic aspects. Very little information appears to exist as to whether, and to what extent, such organic compounds can influence the properties of the macromolecule. Poly vinyl chloride (PVC) is one of the most versatile plastics. It is the second largest manufactured resin by volume worldwide [4]. Recently, scientists were able to modify PVC by introduction aromatic and heterocyclic moieties through halogen displacement reaction. PVC, thus modified, showed improved overall optical properties [5,6]. In recent years, studies on the electrical and optical properties of polymers have attracted much attention in view of their applications in optical devices with remarkable reflection, antireflection, interference and polarisation properties [7-9]. The optical properties of polymers can be suitably modified by the addition of dopants depending on their reactivity with the host matrix. The incorporation of amines in a polymeric system may be expected to enhance its electrical and optical performance. In this paper, we present

results of such a study on the optical properties of pure and other polymers PVC films.

Experimental

Materials and Methods

Synthesis of PVC –amine compounds by dissolving (0.1 g) of PVC in dry THF (20 ml), then add (0.05 mole) from appropriate amine [10]. The reaction mixture was heated under reflux for (3-6)h. The hot mixture was transferred to pitredish, the precipitate modified polymer separated as film by evaporated the solvent. The color prepared polymer and time of reflux are found in Table (1).

Table (1).

<i>Amine (Ligand)</i>	<i>Time reflux</i>	<i>Polymer Color</i>
4-methyl aniline	3	Pal yellow
Di benzyl amine	3	Brown
Penta methylene amine	3	Brown
Benzyl amine	6	Yellow
Aniline	6	Pal yellow


Films Preparation

0.5% concentrations of PVC solution in THF was used to prepare 30 micrometer thickness of polymer films, (measured by a micrometer type 2610 A, Germany). The films were prepared by evaporation technique at room temperature for 24 h. To remove the possible residual tetrahydrofuran solvent, film samples were further dried at room temperature for three hours under reduced pressure. The optical absorbance (A) of the

sample was measured as a function of wavelength (λ) ranged from 200 to 400 nm by using computerized Shimadzu Uv-vis 160A-Ultraviolet-spectrophotometer full-scale absorbance up to (2.5). The light sources are halogen lamp and socket-deuterium lamp. The detector is Si-photodiode and all measurements were performed at room temperature. UV/VIS absorption spectroscopies were made for prepared samples before and after conjunction. The spectra were used to carry out the energy gap by plotting $(\alpha h\nu)^2$ versus $(h\nu)$ with (r) value (1/2) which indicates a transition of direct type. The linear portion was best fitted with $(r=1/2)$ Energy gap shift for all samples plotted as a function to conjunction type [11].

Results and Discussion

The reaction was initiated by the nucleophilic attack of (N) atom on the carbon carrying chlorine atom in the polymeric chain followed by departure of chloride anion as a good leaving group.









The structure of the modified polymers was established on the basis of its FTIR and UV-Vis spectroscopy, each of the present polymers showed other bands characteristic of its own structure.

The successful modification of PVC with different amines can be demonstrated by FTIR spectroscopy. absence of absorption bands due to $(-\text{NH}_2)$ stretching frequencies of amines, clearly indicated the reaction between PVC and amines. These compounds clearly revealed the three characteristic vibrations of the $\text{C}=\text{N}$, $\text{N}-\text{H}$. The most common bands are tabulated in Table (2). The ultraviolet-visible spectrophotometry technique is used to characterize the prepared polymers in (THF) as a solvent. The ultraviolet visible electronic spectra of the prepared compounds and modified polymers showed an absorption bands could be attributed to the $\pi \rightarrow \pi^*$ electronic transitions, these transitions are

assigned in relevance to the structures of compounds and polymers. As shown in Table (2). The increase of the absorbance in the Uv-Vis range for samples containing prepared compounds or modified PVC compared with (PVC) can be explained by the formation of conjugation double bonds (band corresponding to the $\pi \rightarrow \pi^*$ transition) in these modified polymers resulting from introducing an aromatic rings. Thus, shifting the absorbance to longer wavelengths (i.e the bathochromic effect) is good evidence that modification were formed in our PVC and compounds. On the basis of the preceding discussion, the structure of the modified polymers suggested as shown in Table (2).

Table (2)
Characteristic IR absorption bands of Modified polymers, Electronic spectra and suggested structure.

Compound	IR (cm ⁻¹)	Assignments	Absorption Bands (nm.)	Suggested Structure
PVC	2910 612	C-H C-Cl	258	
P1	3245 3173 2923 1601 619	N-H (-C=C-H) C-H aliphatic (C=C) C-Cl	290	
P2	3048 2916 1637 622	C-H (aromatic) , (C-H) alken C-H (aliphatic) C-Cl	276	
P3	2918 612	C-H (aliphatic) C-Cl	283	
P4	3276 2111 2923 1645 646	N-H C-H (aromatic) C-H (aliphatic) N-H (bending) C-Cl	283	
P5	3318 3087 2911 611	N-H C-H (aromatic) C-H (aliphatic) C-Cl	252	

The relation between $(\alpha h\nu)^2$ versus photon energy for the PVC samples are shown in Fig.(1 to 6) for allowed transition. For polymer samples shown in Figs. (2 to 6), the shift in the energy gap could be attributed to the formation of polarons in the films. The evidence of Polaron formation is made that the reaction in band to band transition due to shifting the band density of state toward the energy gap. This observation is not similar to the doping in conventional semiconductors when the band to band absorption strength does not affected by

the formation of dopant state in the energy gap. The effect of the organic addition on the values of phonon energies is also investigated and the results are shown in Table (3). The results presented in Figs. (1 to 6) indicate the existence of two polaron bands in the energy gap. The first one represents the transition from valance band to bonding polaron band. The second band represents the transition from valance band to anti-bonding polaron band, which is in a good agreement with results, are obtained by [12,13and 8]. The Energy gaps

were measured as behavior of a conductivity measurement of PVC with and without additive can obtain by adopting the data of energy gap, (see Table (3) and Figs. from (1 to 6). The conductivity measurement for PVC in the presence of additive increase in the following order. PVC, P1, P3, P5, P2, P4, P5.

Table (3)

Indicate the energy band gap according to the direct allowed transition.

Polymer	E_g (eV)
PVC	5.39
P1	5.05
P2	4.49
P3	4.79
P4	4.3
P5	4.55




Fig.(1) Allowed direct transition $(ah\nu)^2$ Vs Energy for pure PVC.




Fig. (2) Allowed direct transition $(ah\nu)^2$ Vs. Energy for the sample P1.




Fig. (3) Allowed direct transition $(\alpha h\nu)^2$ Vs. Energy for the sample P2.




Fig. (4) Allowed direct transition $(\alpha h\nu)^2$ Vs. Energy for the sample P3.




Fig. (5) Allowed direct transition $(\alpha h\nu)^2$ Vs. Energy for the sample P4.




Fig. (6) Allowed direct transition $(ahv)^2$ Vs. Energy for the sample P5.

Conclusion

The optical absorption in the UV-visible region for PVC polymer with different amines. The Energy gaps were measured as behavior of conductivity and it is conceded that the energy is affected by type of polymer prepared.

References

- [1] Amit, B., Rawlins, J.W., Ray, P., Polymer Crafting and Crosslinking. JOHN WILEY & SONS, INC. 2009.
- [2] Gustafsson B., Hakansson B., Jagner S., "Complexes between copper(I) chloride and polydentate aromatic amines". Inorganica Chimica Acta, vol. 350, pp. 209-214. 2003.
- [3] Genhua Z. and Pan C., Preparation of star polymers based on polystyrene or poly(styrene-*b*-Nisopropyl acrylamide) and divinylbenzene via reversible addition-fragmentation chain transfer polymerization. Polymer, vol. 46, pp. 2802-2810. 2005.
- [4] Claudiu, L., Edina R., Bogdan M., Teodora Z, Gheorghe H., Chemical modification of PVC for polymer matrices with special properties. U.P.B. Sci. Bull., Series B, 72, 127-140. 2010.
- [5] Yousif E., Hameed A. and E. Bakir E., Synthesis and photochemical study of poly(vinyl chloride)-1,3,4-oxadiazole and 1,3,4-thiadiazole, Journal of Al-Nahrain University(Science), vol.10, pp. 7-12. 2007.
- [6] Aliwi M., Yousif E., Otaiwi A., Synthesis and photochemical study of some metal complexes of poly (vinyl chloride)-2-mercapto-5-phenyl 1,3,4-oxadiazole. Iraqi Journal of polymers, vol. 10, pp. 53-64. 2005.
- [7] V. Reddy, Q. Zhu, L. Mai1 and W. Chen, Optical, electrical and discharge profiles for (PVC + NaIO₄) polymer electrolytes. Journal of Applied Electrochemistry, vol. 36, pp. 1051-1056. 2006.
- [8] Al-Ramadin Y., Optical properties of poly(vinyl chloride)/poly(ethylene oxide) blend. Optical Materials, vol. 14, pp. 287-290. 2000.
- [9] Tauc j., Amorphous and Liquid Semiconductor", Plenum Press, London, New York. 1974.
- [10] Yousif E., Hameed A., Kamil A., Farina Y., Asaad N., and Graisa A., Synthesis of New Polymers Derived from Poly (vinyl Chloride) and Study Their Biological Evaluation, Australian Journal of Basic and Applied Sciences, vol. 3, pp.1786-1794. 2009.
- [11] Yousif, E. O. Hassan, A. Otaiwi and Farina Y., Studying the conductivity of Poly(vinyl chloride) using 2-thioacetic acid benzothiazole complexes as additives by measuring forbidden energy gap. Iraqi Journal of polymers, vol. 12, pp.5-78. 2008.
- [12] Yousif E., Abdul Nabi M. and Aliwi S., Optical properties modification of polystyrene films by 2N-salicylidene-5-(p-nitro phenyl)-1,3,4-thiadiazole complexes. Journal of Al-Nahrain University, vol. 8, pp. 22-26. 2005.

- [13]Abdul Nabi M, Yousif E., Alwash A., and Farina Y., Optical properties modification of Poy(vinyl chloride) using Complexes of 2-Amino-5- (2-acetyloxyphenyl)-1,3,4 – thiadiazole. Iraqi Journal of polymers, vol. 13, pp. 27-63. 2009.

الخلاصة

تم مفاعلة بولي فنيل كلورايد مع امينات مختلفة بوجود التتراهيدرو فيوران كمذيب. تم تشخيص البوليمرات الجديدة باستخدام الطرق الطيفية Uv-Vis و IR. تم دراسة الخصائص البصرية للبوليمرات في المنطقة 200-400 nm ومن خلال حساب فجوة الطاقه استنتجنا توصيليه البوليمرات الجديدة.